

Study on the Preparation of Silica Using Residues of Oil Shale

DOI: 10.15255/KUI.2015.008

KUI-20/2015

Original scientific paper

Received February 5, 2015

Accepted May 19, 2015

*L. Nie and T. Wang**

College of Construction Engineering, Jilin University, 6 Xi Min Zhu Street, Changchun 130 026, Jilin Province, P.R. China

Abstract

Usage of oil shale produces abundant oil shale residue, which may not only directly cause serious pollution to the environment, but also result in a waste of resource. In this paper, acid leaching method and alkali soluble method were compared to obtain the optimum processing conditions for the preparation of white carbon black, which was determined as follows: the mass fraction of NaOH was 8 %, the alkali dissolving time was 5 h, and the reaction temperature was 100 °C. Then the performance characteristics of the obtained white carbon black were analysed by XRD, SEM and IR spectroscopy. The results showed that the product of silica has a particle size between 20 – 30 nm and a purity of 98.4 %. Preparation of the high quality white carbon black might be a good way to make sufficient and reasonable use of oil shale residues, which will bring many environmental and social benefits.

Keywords

Residue of oil shale, silica, alkali dissolving, characterization

1. Introduction

With the increasing demands for energy and reduction of available petroleum resources, the long-term oil prices tend to increase. Oil shale has drawn much attention in recent years as an important alternative energy resource. However, the waste residue from each oil shale extraction method is fairly high. Even concerning the maximum oil content of oil shale (around 30 %), there will be 70 % waste residue of the spent oil shale after retorting.¹ The main components of oil shale waste are SiO₂, Al₂O₃, Fe₂O₃, MgO, CaO and SO₃ etc. Besides, there are many kinds of trace elements, including poisonous and harmful elements.² China and the United States have the largest oil shale ash heap in the world, but now there are only Estonia, Russia, Germany and another six countries utilizing the ash and slag. The analysis of the ash shows that it contains heavy metal elements and trace amounts of radioactive elements, which are very likely to cause pollution in water, soil and surrounding flora and fauna. How to effectively improve the comprehensive utilization of oil shale ash and increase the added value of oil shale resources is a technical problem to be solved.

White carbon black is a porous, white, amorphous substance with a large internal surface area, which has good resistance to acids, and is insoluble in water and acids (except for hydrofluoric acid). It is a kind of promising fine chemical widely used in rubbers, plastics, agrochemicals, paintings, medicines, and so on.⁴⁻⁶

Reports on the use of oil shale residue to make silica are prevalent in recent years. However, the experimental results turn out to be not good, and especially the low pu-

riety of the product seriously affects its application performance.⁷⁻⁹ Therefore, in order to improve the application performance of silica generated from oil shale residue, further improvement of the preparation method is necessary.

2. Materials and methods

2.1. Oil shale samples

The oil shale used in this study was obtained from the open pit mine located in Fu Shun (FS), China. It was received as hard, dark grey blocks with no particular smell. After burning, breaking, and lapping, the samples were prepared. The chemical composition of the oil shale residue was obtained by X-ray fluorescence spectrometer (Table 1), in which SiO₂ accounted for more than 60 % of the oil shale residue.

Table 1 – Chemical composition of the semicoke of oil shale analysed by XRF

Tablica 1 – Kemijski sastav polukoksa naftnog škrljevca analiziran XRF-om

Component Sastojak	w / %
SiO ₂	63.52
Al ₂ O ₃	26.21
Fe ₂ O ₃	3.13
TiO ₂	0.78
CaO	4.31
MgO	0.22
K ₂ O	1.08
Na ₂ O	0.76



* Corresponding author: Dr. Tong Wang
e-mail: wangt1455@163.com

2.2. Comparison of alkaline and acid methods

2.2.1. The preparation of silica by acid method

In the acid dissociation method, metal oxides and H_2SO_4 reacted easily to produce soluble metal ions, so that Al_2O_3 , Fe_2O_3 could be separated from SiO_2 after filtration. In addition, SiO_2 changed from crystal structure to amorphous structure and silica was obtained.

The reaction equations are:



Sulfuric acid of a certain concentration was added into a round-bottom flask, preheated to 90°C in a constant temperature water bath, with the quick addition of 10 g of the calcined oil shale residue and magnetically stirred.¹⁰⁻¹⁶

In order to study the influence of the concentration of H_2SO_4 on the leaching rate of SiO_2 , adopted were four different concentrations of H_2SO_4 analysis. The outcomes of different concentrations of H_2SO_4 are shown in Table 2.

Table 2 – Leaching rates of SiO_2 at different concentrations of H_2SO_4



Tablica 2 – Brzine izluživanja SiO_2 pri različitim koncentracijama H_2SO_4

$c(\text{H}_2\text{SO}_4)/\text{mol l}^{-1}$	Leaching rate of $\text{SiO}_2/\%$ Brzina izluživanja $\text{SiO}_2/\%$
1.0	18.3
5.0	28.5
8.5	42.3
10.0	44.2

The results showed that the leaching rate of SiO_2 increased along with the concentration of H_2SO_4 . When the concentration of H_2SO_4 was low, not only was the leaching rate of silica low, but also the silica colour was not white, suggesting the quality of the product was low. When 1.0 ml H_2SO_4 was used, the colour of the obtained silica was earthy red, indicating Fe^{3+} existed in the white carbon black. The acid dissociation method can exclude Fe^{3+} from the oil shale, thus it can influence the quality of obtained silica effectively.

2.2.2. Preparation of silica by alkaline method

Alkali method mainly uses the reaction of oil shale ash, SiO_2 , Al_2O_3 and NaOH to generate water soluble Na_2SiO_3 , and separate the Na_2SiO_3 from the other components of the oil shale ash by filtration. To carry out the reaction successfully, the solution pH has to be controlled in a certain range. The reaction equations are:



In the reaction, 10 g oil shale ash, 30 ml water, and 15 g NaOH was added into a 250 ml three-neck flask, and heated at 95°C in a water bath to react for about 2 h. The pH

was adjusted to 8 – 9 to produce white floc, then filtered. The rest of the residue was the white carbon black.¹⁷⁻²³

In order to study the influence of the concentration of NaOH on the leaching rate of SiO_2 , reactions were carried out in different concentrations of NaOH , and the leaching rates of SiO_2 are shown in Table 3.

Table 3 – Leaching rates of SiO_2 at different concentrations of NaOH

Tablica 3 – Brzine izluživanja SiO_2 pri različitim koncentracijama NaOH

$c(\text{NaOH})/\text{mol l}^{-1}$	Leaching rate of $\text{SiO}_2/\%$ Brzina izluživanja $\text{SiO}_2/\%$
0.8	10.2
1.8	35.4
2.8	40.3
3.8	52.8
5.0	58.2

Results showed that the alkali concentration had a significant effect on the leaching rate of SiO_2 (Table 3). By comparing the results listed in Table 2 and Table 3, it can be seen that the prepared silica by alkaline method was much higher than that with the acid extraction method. The alkaline dissolution method is more suitable for the industrial production of silica, so this study adopted the alkali dissolving methods to analyse the influence factors of the silicon extraction rate.

2.3. Influence factors of the alkali dissolving method

2.3.1. Influence of the dissociation temperature

To investigate the influence of dissociation temperature on the leaching rate of SiO_2 , the reaction temperature was changed to perform the preparation. The results indicated that by increasing the reaction temperature, the extraction rate of SiO_2 had also increased (Fig. 1), which might be attributed to the improved diffusion and chemical reaction rates at higher temperature.




Fig. 1 – Influence of alkali solution temperature on the SiO_2 extraction rate

Slika 1 – Utjecaj temperature lužnate otopine na brzinu ekstrakcije SiO_2

The extraction rate of SiO_2 increased rapidly with temperature up to 90°C , while it became stable in the range of $90\text{--}100^\circ\text{C}$. Considering the industrial steam heating, 100°C might be the optimum extraction temperature.

2.3.2 Influence of the dissociation time

The effect of dissociation time was investigated at various times. As the reaction time proceeded, the extraction rate of SiO_2 increased in the first 5 h, after which it declined. A plausible explanation for this may be due to the separation of Si from the lattice, as the reaction lasted over 5 h, and silicic acid precipitated on the remaining mineral surface, thus slowing down the reaction. Therefore, the appropriate dissociation time for the alkali might be 5 h.




Fig. 2 – Influence of dissociation time on the SiO_2 extraction rate
Slika 2 – Utjecaj vremena disocijacije na brzinu ekstrakcije SiO_2

2.3.3. Determination of the amount of NaOH

The effect of the concentration of NaOH on the extraction rate was investigated.




Fig. 3 – Effect of the mass fraction of NaOH on the SiO_2 extraction rate
Slika 3 – Učinak masenog udjela NaOH na brzinu ekstrakcije SiO_2

The results showed that the leaching rate increased as the mass fraction of NaOH increasing up to 8 %. When the mass fraction of NaOH was over 8 %, the extraction rate noticeably declined (Fig. 3). Extracting silica with sodium hydroxide is a solid-liquid multiphase chemical reaction, which may be controlled by diffusion or chemical reaction. In either case, the leaching rate is proportional to the concentration of sodium hydroxide. Because a portion of silica may be attached on the surface of the aluminum dross, the concentration of NaOH should be low; otherwise, the solution will exhibit high viscosity, resulting in difficulties in solid-liquid separation, and thus influencing the extraction rate.

3. Results and discussion

Silica as an important inorganic chemical raw material in industry that has many product indicators, including the contents of impurities, silicon dioxide, and so on. The performance characteristics of the obtained silica in this research was analysed by XRD spectrum, IR spectrum and SEM.^{24–25}

3.1. Purity analysis

The purity of the product was analysed by X-ray fluorescence spectrometry, as shown in the following Table 4.

Table 4 – Composition of the silica obtained by the alkali dissolving method

Tablica 4 – Sastav silicijeva dioksida pripremljenog metodom otapanja lužinom

Component Sastojak	w/%
SiO_2	98.4
Al_2O_3	0.124
Fe_2O_3	0.456
TiO_2	0.099
CaO	0.134
MgO	0.086
Cl	0.111
ZnO	0.014
SO_3	0.144
Na_2O	0.428

Results showed that there were very low amounts of impurities in the product.

3.2. XRD analysis

The crystal structure of the product recognition with XRD is shown in Fig. 4.




Fig. 4 – XRD spectrum of the silica product
Slika 4 – XRD-spektar proizvoda silicijeva dioksida

The XRD spectrum of the SiO_2 product did not show a sharp crystal diffraction peak, while only amorphous diffraction peaks appeared at $20 - 30^\circ$, indicating that the obtained products contained no other crystalline phases, and the product structure was amorphous.

3.3. IR analysis

In the infrared spectrum, the 1100 cm^{-1} and 466 cm^{-1} peaks represented the Si–O–Si bond of antisymmetric stretching vibration, while the peak at 950 cm^{-1} represented the bending vibration. The 1640 cm^{-1} absorption peak indicated the bending vibration of surface water H–O–H. The peak at 3400 cm^{-1} indicated the product internal structure of water (Fig. 5).




Fig. 5 – Infrared spectrum of the silica product
Slika 5 – Infracrveni spektar proizvoda silicijeva dioksida

3.4. SEM analysis

The results of the scanning electron microscope analysis of the product is shown in Fig. 6.




Fig. 6 – Scanning electron microscopy image of the silica product

Slika 6 – Slika proizvoda silicijeva dioksida snimljena skenirajućom elektronskom mikroskopijom

The SEM image showed that the product was in aggregation and the outline was not clear, which might be due to the internal temperature gradient of silica in the process of heating. Dehydration between the hydroxyl functional groups (OH–Si–OH) caused the aggregation of the particles, whose size was between $20 - 30 \text{ nm}$.

4. Conclusions

The alkali dissociation method is more suitable for the preparation of silica from oil shale residues than the acid dissociation method, because it results in a higher yield of SiO_2 .

The optimum conditions for the preparation of silica from FS oil shale residue are as follows: temperature 100°C , mass fraction of NaOH 8 %, and alkali dissolving time 5 h.

Through XRD, IR and SEM analysis, it was found that the produced silica had a purity of 98.4 % and a particle size between $20 - 30 \text{ nm}$, indicating the product is high-quality white carbon black.

List of symbols and abbreviations**Popis simbola i kratica**

- θ – scattering angle
– kut raspršenja
- IR – infrared radiation
– infracrveno zračenje
- XRD – x-ray diffraction
– rendgenska difrakcija
- XRF – x-ray fluorescence
– rendgenska fluorescencija
- SEM – scanning electron microscope
– skenirajući elektronski mikroskop

References**Literatura**

1. H.-W. Jing, H.-Z. Liu, An experimental study on agricultural utilization of shale oil industrial soil waste, *Nat. Sci.* **37** (2001) 260–265.
2. A. Raukas, Oil shale industry and sustainability-governance through dialogue, *Oil Shale*. **22** (2005) 3–4.
3. Z.-J. Liu, R. Liu, Oil shale resource state and evaluating system, *Earth Sci. Front.* **12** (2005) 315–322.
4. J.-J. You, Y.-S. Qing, Comprehensive development and utilization of oil shale, *Global J. Geol. Sci.* **23** (2004) 261–265.
5. O. A. Ehinola, O. O. Sonibare, O. A. Akanbi, Economic evaluation, recovery techniques and environmental implications of the oil shale deposit in the Abakaliki anticlinorium, South-eastern Nigeria, *Oil Shale*. **22** (2005) 5–9.
6. D.-H. Peng, J.-I. Qian, Oil shale activities in China, *Oil Shale* **8** (1991) 97–105.
7. Y.-H. Xue, T.-T. Guo, Z. Xue, Research on Preparation of White Carbon Black from Oil Shale Residue by Chemical Way, *Multipurpose Util. Miner. Resour.* **4** (2012) 40–42.
8. T. Kiipli, R. A. Batchelor, J. P. Bernal, C. Cowing, Seven sedimentary rock reference samples from Estonia, *Oil Shale*. **17** (2000) 215–223.
9. J.-G. Na, S.-H. Chung, K.-B. Lee, Effect of oil shale retorting temperature on shale oil yield and properties. *Fuel*. **95** (2012) 131–135, doi: <http://dx.doi.org/10.1016/j.fuel.2011.11.029>.
10. S.-H. Deng, Z.-J. Wang, Q. Gu, F.-Y. Meng, J.-F. Li, H.-Y. Wang, Extracting hydrocarbons from Huadian oil shale by sub-critical water, *Fuel Process. Technol.* **92** (2011) 1062–1067, doi: <http://dx.doi.org/10.1016/j.fuproc.2011.01.001>.
11. The national standard of the People's Republic of China, GB/T 13377; 2010 [Chinese].
12. The national standard of the People's Republic of China (Standard for soil test method) GB/T 50123; 1999 [Chinese].
13. X.-M. Jiang, X.-X. Han, Z.-G. Cui, Progress and recent utilization trends in combustion of Chinese oil shale, *Prog Energy Combust. Sci.* **33** (2007) 552–579, doi: <http://dx.doi.org/10.1016/j.pecs.2006.06.002>.
14. M. V. Kök, Effect of clay on crude oil combustion by thermal analysis techniques. *J. Therm. Anal. Calorim.* **84** (2006) 361–366, doi: <http://dx.doi.org/10.1007/s10973-005-7153-2>.
15. W. Henderson, G. Eglinton, P. Simmonds, J. E. Loveloc, Thermal alteration as a contributory process to the genesis of petroleum, *Nature*. **219** (1968) 1012–1016, doi: <http://dx.doi.org/10.1038/2191012a0>.
16. B. E. Scheetz, White Vibrational spectra of the alkaline earth double carbonates. *Am. Mineral* **62** (1977) 36–50.
17. K. Grice, S. Schouten, P. Blokker, S. Derenne, C. Largeau, A. Nissenbaum, Structural and isotopic analysis of kerogens in sediments rich in using thermal, X-ray and IR techniques, *Fuel* **84** (2005) 707–715, doi: <http://dx.doi.org/10.1016/j.fuel.2004.11.013>.
18. X.-Y. Qu, L. Liu, R. Ma, D.-Q. Hu, X. Chen, Y.-M. Wang, Experiment on debris-arkosic sandstone reformation by CO₂ fluid, *J. Jilin Univ.* **38** (2008) 959–964.
19. G. R. L. Chalmers, D. K. Ross, R. M. Bustin, Geological controls on matrix permeability of Devonian Gas Shales in the Horn River and Liard basins, Northeast British Columbia, Canada. *Int. J. Coal. Geol.* **103** (2012) 120–131, doi: <http://dx.doi.org/10.1016/j.coal.2012.05.006>.
20. M. F. Martins, S. Salvador, J. F. Thovert, G. Debenest, Co-current combustion of oil shale-Part 1: Characterization of the solid and gaseous products, *Fuel* **89** (2010) 144–151, doi: <http://dx.doi.org/10.1016/j.fuel.2009.06.036>.
21. O. Gavrilova, R. Vilu, L. Vallner, A life cycle environmental impact assessment of oil shale produced and consumed in Estonia, *Resour. Conserv. Recy.* **55** (2010) 232–245, doi: <http://dx.doi.org/10.1016/j.resconrec.2010.09.013>.
22. X.-M. Jiang, X.-X. Han, Z.-G. Cui, Progress and recent utilization trends in combustion of Chinese oil shale, *Prog. Energy Combust. Sci.* **33** (2007) 552–579, doi: <http://dx.doi.org/10.1016/j.pecs.2006.06.002>.
23. M. J. Adams, F. Awaja, S. Bhargava, S. Grocott, M. Romeo, Prediction of oil yield from oil shale minerals using diffuse reflectance infrared Fourier transform spectroscopy, *Fuel*. **84** (2005) 1986–1991, doi: <http://dx.doi.org/10.1016/j.fuel.2005.04.011>.
24. L.-H. Liu, Y. Suto, G. Bignall, N. Yamasaki, T. Hashida, CO₂ injection to granite and sandstone in experimental rock/hot water systems, *Energy Convers. Manage.* **44** (2003) 1399–1410, doi: [http://dx.doi.org/10.1016/S0196-8904\(02\)00160-7](http://dx.doi.org/10.1016/S0196-8904(02)00160-7).
25. B. Liang, B. Lan, J.-G. Wang, Tri-axial compression test study on mechanical characteristics of oil shale under the water, *J. Shandong Univ.* **41** (2011) 82–85.

SAŽETAK

Studija o pripravi silicijeva dioksida uporabom ostataka iz naftnih škriljevaca

*Lei Nie i Tong Wang**

Uporabom naftnih (uljnih) škriljevaca nastaje obilje ostataka naftnog škriljevca, koji ne samo da mogu izravno uzrokovati ozbiljno onečišćenje okoliša, već i dovesti do gubitka resursa. U ovom radu provedena je usporedba metode izluživanja kiselinom i metode otapanja lužinom kako bi se dobili optimalni uvjeti za obradu i dobivanje bijele čađe, koji su određeni na sljedeći način: maseni udjel NaOH je 8 %, vrijeme otapanja u lužini je 5 h i temperatura reakcije 100 °C. Potom su analizirane karakteristike dobivene bijele čađe pomoću XRD-a, SEM-a i IR spektroskopije. Rezultati su pokazali da proizveden silicijev dioksid ima veličinu čestica 20 – 30 nm i čistoću od 98,4 %. Priprava visokokvalitetne bijele čađe dobar je način za postizanje dovoljnog i razumnog korištenja ostataka naftnog škriljevca, koje može imati brojne ekološke i društvene koristi.

Ključne riječi

Ostatci naftnog škriljevca, silicijev dioksid, otapanje lužinom, karakterizacija

*College of Construction Engineering
Jilin University, 6 Xi Min Zhu Street
Changchun 130 026
Jilin Province
Kina*

*Izvorni znanstveni rad
Prispjelo 5. veljače 2015.
Prihvaćeno 19. svibnja 2015.*