

CALCULATION OF THERMODYNAMIC PROPERTIES OF EARTH METALS – COPPER-ZINC (Cu-Zn)

Received – Priljeno: 2020-11-30
Accepted – Prihvaćeno: 2021-03-10
Review Paper – Pregledni rad

The approximate methods calculated the standard thermodynamic characteristics of our new obtained copper-zinc manganites of compositions of $\text{LaMeI}_2\text{CuZnMnO}_6$ and LaMeII CuZnMnO_6 (MeI – Li, Na, K; MeII – Mg, Ca, Sr, Ba).

Keywords: alkaline earth metals, thermodynamic properties, lanthanum, copper, zinc

INTRODUCTION

The literature data presents that cuprates, manganites, zincates of the rare-earth elements substituted with oxides of the alkali and alkaline-earth metals have a certain scientific and practical importance for the inorganic materials science because of their promising physico-chemical properties and compounds based on manganese alloys are widely used in metallurgy [1-7].

WAYS OF STUDY

In connection with the above-stated this paper demonstrates the results of calculation of the standard thermodynamic properties of our first synthesized nanostructured quadruple copper-zinc manganites of lanthanum, alkali and alkaline-earth metals of the compositions of $\text{LaMeI}_2\text{CuZnMnO}_6$ and LaMeII CuZnMnO_6 (MeI – Li, Na, K; MeII – Mg, Ca, Sr, Ba). The high-temperature synthesis of the mentioned manganites was performed with the ceramic technology in the interval of 800-1200 °C similar to [5] from La_2O_3 (“especially pure”), ZnO , CuO , Mn_2O_3 and carbonates of the alkali and alkaline earth metals (qualification “analytically pure”).

The low temperature annealing was performed to obtain the low temperature equilibrium phases at 400 °C. The obtained new phases were ground to the nanostructured particles on the Retsch MM301 vibration mill (Germany) and their sizes were determined on the electron microscope MJRA3, LMU Tescan. The X-ray analysis of the samples was performed on the DRON-2.0. It was determined that all test compounds were crystallized in the cubic syngony.

B.K. Kasenov (e-mail: kasenov1946@mail.ru), Sh.B. Kasenova, Zh.I. Sagintaeva, E.E. Kuanyshbekov, A.A. Mukhtar, Chemical-Metallurgical Institute, Karaganda,
B.T. Ermagambet, Institute of Coal Chemistry and Technology, Nur-Sultan, Kazakhstan

Referring to the above-mentioned, the objective of this paper is to calculate the standard thermodynamic characteristics of our obtained compounds, which are of interest for processes with their use and for their directed synthesis. The thermodynamic constants of the new compounds are the initial information collection for the fundamental reference books and data banks of the thermodynamic constants. It should be noted that our investigation of the physical and chemical properties of some similar cobalte (nickelite) -cuprate-manganites of lanthanum, the alkali and alkaline earth metals were published in papers of [8, 9].

In order to calculate the values of the standard enthalpies of formation of the test compounds, our developed method was used to calculate the standard enthalpy of formation of the double and triple manganites of the rare earth, alkali and alkaline earth metals of composition of $\text{LnMeI}_3\text{MeII}_3\text{Mn}_4\text{O}_{12}$ (MeI – alkali, MeII – alkaline earth, Ln – rare earth metals) [5, 10, 11].

The calculation method is as follows:

– The similarity coefficient K_1 was calculated from the ratio of

$$K_1 = \frac{\Delta_f H^\circ(298,15) \text{Ln}(\text{MnO}_4)_3}{\Delta_{\text{ok}} H^\circ(298,15) \text{Ln}(\text{MnO}_4)_3} \quad (1)$$

where $\Delta_f H^\circ(298,15) \text{Ln}(\text{MnO}_4)_3$ – a standard enthalpy of formation of permanganate of the rare-earth metals from the simple substances, $\Delta_{\text{ok}} H^\circ(298,15) \text{Ln}(\text{MnO}_4)_3$ – a sum of the enthalpy of formation from simple oxides or the conditionally taken standard enthalpy of formation of permanganate of the rare earth metals from oxides, is equal to

$$\begin{aligned} \Delta_{\text{ok}} H^\circ(298,15) \text{Ln}(\text{MnO}_4)_3 &= \\ &= 0,5 \Delta_f H^\circ(298,15) \text{Ln}_2\text{O}_3 + \\ &+ 1,5 \Delta_f H^\circ(298,15) \text{Mn}_2\text{O}_7. \end{aligned} \quad (2)$$

– Then the similarity coefficient K_2 was calculated under the equation of

$$K_2 = \Delta_f H^\circ(298,15) \text{ MeIMnO}_4 / \Delta_{\text{ok}} H^\circ(298,15) \text{ MeIMnO}_4, \quad (3)$$

where $\Delta_{\text{ok}} H^\circ(298,15) \text{ MeIMnO}_4$ – a standard enthalpy of formation of permanganate of alkali metal from oxides is equal to

$$\begin{aligned} \Delta_{\text{ok}} H^\circ(298,15) \text{ MeIMnO}_4 &= \\ &= \Delta_f H^\circ(298,15) \text{ Me}_2\text{O} + \\ &+ 0,5 \Delta_f H^\circ(298,15) \text{ Mn}_2\text{O}_7 \end{aligned} \quad (4)$$

– The similarity coefficient K_3 was calculated from the ratio of

$$K_3 = \Delta_f H^\circ(298,15) \text{ MeII}(\text{MnO}_4)_2 / \Delta_{\text{ok}} H^\circ(298,15) \text{ MeII}(\text{MnO}_4)_2 \quad (5)$$

where $\Delta_{\text{ok}} H^\circ(298,15) \text{ MeII}(\text{MnO}_4)_2$ – a standard enthalpy of formation of permanganate of the alkaline earth metal from oxides is equal to

$$\begin{aligned} \Delta_{\text{ok}} H^\circ(298,15) \text{ MeII}(\text{MnO}_4)_2 &= \\ &= \Delta_f H^\circ(298,15) \text{ MeO} + \\ &+ \Delta_f H^\circ(298,15) \text{ Mn}_2\text{O}_7. \end{aligned} \quad (6)$$

– The average similarity coefficient \bar{K} was calculated from:

$$\bar{K} = (K_1 + K_2 + K_3) / 3 \quad (7)$$

– $\Delta_{\text{ok}} H^\circ(298,15) \text{ LnMeI}_3 \text{ MeII}_3 \text{ Mn}_4 \text{ O}_{12}$ was calculated from:

$$\begin{aligned} \Delta_{\text{ok}} H^\circ(298,15) \text{ LnMeI}_3 \text{ MeII}_3 \text{ Mn}_4 \text{ O}_{12} &= \\ &= 0,5 \Delta_f H^\circ(298,15) \text{ Ln}_2\text{O}_3 + \\ &+ 1,5 \Delta_f H^\circ(298,15) \text{ Me}_2\text{O} + \\ &+ 3 \Delta_f H^\circ(298,15) \text{ MeO} + \\ &+ 2 \Delta_f H^\circ(298,15) \text{ Mn}_2\text{O}_3 \end{aligned} \quad (8)$$

– Similar to equations of (1, 3, 5), the ratio can be described as:

$$\bar{K} = \Delta_f H^\circ(298,15) \text{ LnMeI}_3 \text{ MeII}_3 \text{ Mn}_4 \text{ O}_{12} / \Delta_{\text{ok}} H^\circ(298,15) \text{ LnMeI}_3 \text{ MeII}_3 \text{ Mn}_4 \text{ O}_{12} \quad (9)$$

where it can be calculated as

$$\begin{aligned} \Delta_f H^\circ(298,15) \text{ LnMeI}_3 \text{ MeII}_3 \text{ Mn}_4 \text{ O}_{12} &= \\ &= \bar{K} \Delta_{\text{ok}} H^\circ(298,15) \text{ LnMeI}_3 \text{ MeII}_3 \text{ Mn}_4 \text{ O}_{12} \end{aligned} \quad (10)$$

In connection with the absence of the reference date on $\Delta_f H^\circ(298,15)$ manganites, the first approximate values \bar{K} were calculated from data on $\Delta_f H^\circ(298,15)$ permanganates, which used to calculate $\Delta_f H^\circ(298,15)$ of the test compounds. Thus it was taken into account that the values \bar{K} of manganites are not differ much from permanganates \bar{K} .

Based on the above-said and taken the ratios of (11, 12) for the copper-zinc manganites of lanthanum, the alkali and alkaline earth metals, the following ratios can be demonstrated as:

$$\begin{aligned} \Delta_f H^\circ(298,15) \text{ LnMeI}_3 \text{ MeII}_3 \text{ Mn}_4 \text{ O}_{12} / \Delta_{\text{ok}} H^\circ(298,15) \text{ LnMeI}_3 \text{ MeII}_3 \text{ Mn}_4 \text{ O}_{12} &= \\ = \Delta_f H^\circ(298,15) \text{ LaMeI}_2 \text{ CuZnMnO}_6 / \Delta_{\text{ok}} H^\circ(298,15) \text{ LaMeI}_2 \text{ CuZnMnO}_6 \end{aligned} \quad (11)$$

$$\begin{aligned} \Delta_f H^\circ(298,15) \text{ LnMeI}_3 \text{ MeII}_3 \text{ Mn}_4 \text{ O}_{12} / \Delta_{\text{ok}} H^\circ(298,15) \text{ LnMeI}_3 \text{ MeII}_3 \text{ Mn}_4 \text{ O}_{12} &= \\ = \Delta_f H^\circ(298,15) \text{ LaMeIICuZnMnO}_6 / \Delta_{\text{ok}} H^\circ(298,15) \text{ LaMeIICuZnMnO}_6 \end{aligned} \quad (12)$$

Table 1 shows the initial data to calculate the standard enthalpies of formation of the copper-zinc manganites of lanthanum, the alkali and alkaline earth metals [5, 11-17].

Based on data in Table 1, the values of $\Delta_{\text{ok}} H^\circ(298,15)$ were calculated, and $\Delta_f H^\circ(298,15)$ was received with using of the values \bar{K} (Table 2).

The coefficient \bar{K} for LaLi and LaMg was equal to 1,2375, LaNa and LaCa – 1,3084, LaK and LaSr – 1,3545, LaBa – 1,3703. The accuracy of calculation was $\pm 5,0 \%$.

Table 1 **The initial data to calculate the standard enthalpies of formation of the copper-zinc manganites of lanthanum, the alkali and alkaline earth metals [5, 11-17]**

Compounds	$-\Delta_{\text{ok}} H^\circ(298,15) / \text{kJ/mol}$	\bar{K}	$-\Delta_f H^\circ(298,15) / \text{kJ/mol}$	References
$\text{LaLi}_3 \text{ Mg}_3 \text{ Mn}_4 \text{ O}_{12}$	5 514,4	1,2375	6 824,1	[5, 11]
$\text{LaNa}_3 \text{ Ca}_3 \text{ Mn}_4 \text{ O}_{12}$	5 340,5	1,3084	6 987,5	-/-
$\text{LaK}_3 \text{ Sr}_3 \text{ Mn}_4 \text{ O}_{12}$	5 127,3	1,3545	6 944,8	-/-
$\text{LaRb}_3 \text{ Ba}_3 \text{ Mn}_4 \text{ O}_{12}$	4 965,6	1,3703	6 804,3	-/-
Li_2O			593,94	[12]
Na_2O			414,84	[12]
K_2O			362,33	[13]
MgO			601,49	[14]
CaO			635,09	[14]
SrO			590,53	[14]
BaO			548,10	[14]
La_2O_3			1 794,94	[15]
CuO			162,11	[16]
ZnO			350,86	[16]
Mn_2O_3			957,72	[17]

Table 2 The standard thermodynamic characteristics of the copper-zinc manganites of lanthanum, the alkali and alkaline earth metals

Compounds	$-\Delta_f H^\circ(298,15) / \text{kJ} / \text{mol}$	$C_p^\circ(298,15) / \text{J} / (\text{mol}\cdot\text{K})$	$S^\circ(298,15) / \text{J} / (\text{mol}\cdot\text{K})$
$\text{LaLi}_2\text{CuZnMnO}_6$	3 072,2	246,4	245,0
$\text{LaNa}_2\text{CuZnMnO}_6$	3 013,9	258,6	285,2
$\text{LaK}_2\text{CuZnMnO}_6$	3 048,5	261,0	310,4
LaMgCuZnMnO_6	3 073,2	227,2	232,5
LaCaCuZnMnO_6	3 293,6	232,3	248,0
LaSrCuZnMnO_6	3 349,5	234,3	259,0
LaBaCuZnMnO_6	3 330,9	233,4	269,6

The calculation of the standard heat capacities and standard entropies of the test compounds was received with a method of the ionic entropy increments [18]. In order to calculate $C_p^\circ(298,15)$ of the copper-zinc manganites, the following values of the ionic increments (C_p^i) of heat capacity [J / (mol·K)] were used: $\text{Li}^+ - 20,7$; $\text{Na}^+ - 26,8$; $\text{K}^+ - 28,0$; $\text{Mg}^{2+} - 22,2$; $\text{Ca}^{2+} - 27,3$; $\text{Sr}^{2+} - 29,3$; $\text{Ba}^{2+} - 28,4$; $\text{La}^{3+} - 29,3$; $\text{Cu}^{2+} - 25,0$; $\text{Zn}^{2+} - 25,5$; $\text{Mn}^{3+} - 25$; $\text{O}^{2-} - 16,7$; and the values of the ionic entropy increments (S^i) [J / (mol·K)] were used to calculate $S^\circ(298,15)$ of compounds: $\text{Li}^+ - 14,5$; $\text{Na}^+ - 34,6$; $\text{K}^+ - 47,2$; $\text{Mg}^{2+} - 16,5$; $\text{Ca}^{2+} - 32,0$; $\text{Sr}^{2+} - 43,0$; $\text{Ba}^{2+} - 53,6$; $\text{Cu}^{2+} - 36,5$; $\text{La}^{3+} - 40,4$; $\text{Zn}^{2+} - 34,2$; $\text{Mn}^{3+} - 34,7$; $\text{O}^{2-} - 11,7$. Table 2 demonstrates the calculated values of $C_p^\circ(298,15)$ and $S^\circ(298,15)$ of the copper-zinc manganites. The accuracy of calculation referring to [18] was $\pm 3,0\%$.

CONCLUSION

The standard enthalpies of formation of the copper-zinc manganites of lanthanum, the alkali and alkaline-earth metals of compositions of $\text{LaMe}^I_2\text{CuZnMnO}_6$ and $\text{LaMe}^{II}\text{CuZnMnO}_6$ ($\text{Me}^I - \text{Li, Na, K}$; $\text{Me}^{II} - \text{Mg, Ca, Sr, Ba}$) were first calculated with our developed method.

The standard heat capacities and standard entropies of compounds of $\text{LaMe}^I_2\text{CuZnMnO}_6$ and $\text{LaMe}^{II}\text{CuZnMnO}_6$ ($\text{Me}^I - \text{Li, Na, K}$; $\text{Me}^{II} - \text{Mg, Ca, Sr, Ba}$) were first calculated with the method of the ionic increments.

The obtained standard thermodynamic constants of the above mentioned compounds are of interest for their directed synthesis and similar compounds, and also are the initial information collection for the fundamental reference books and databases of the thermodynamic values.

Acknowledgements

This research has been funded by the Science Committee of the Ministry of Education and Science of the Republic of Kazakhstan (Grant No. AP08855601).

REFERENCES

- [1] Yu. D. Tretyakov, O. A. Brylev, The new generation of inorganic functional materials, Russian Journal of General Chemistry 45 (2000) 4, 10-16.
- [2] R. M. Yeremina, K. R. Sharipov, L. V. Mingaliev et al., Investigation of properties of ceramics of $\text{La}_{1-x}\text{Sr}_x\text{Mn}_{0,925}\text{Zn}_{0,075}\text{O}_3$ ($x = 0,075, 0,095, 0,115$), Solid state physics 54 (2012) 6, 1090-1095.
- [3] N. I. Solin, S. V. Naumov, Magnetic and electrical properties of weakly doped manganites of $\text{La}_{1-x}\text{Ca}_x\text{Mn}_{17}\text{O}_3$ with manganese lack, Journal of experimental and theoretical physics 147 (2015) 1, 112-118.
- [4] A. A. Bobitov, A. I. Maximov, V. A. Mozhnikov et al., Nanostructured materials based on zinc oxide for heterostructural solar elements, Physics and semiconductor technology 49 (2015) 10, 1402-1406.
- [5] B. K. Kassenov, Sh. B. Kassenova, Zh. I. Sagintayeva et al., Double and triple manganites, ferrites and chromites of alkali, alkaline-earth and rare-earth metals, M.: Nauchnyi mir, 2017, 416 p.
- [6] S. O. Baysanov, G. G. Gabdulin, T. D. Takenov, On the organization of production of manganese ferroalloy from Kazakhstan raw materials, Steel (1997) 7, 29-32.
- [7] S.O. Baysanov, T.D. Takenov, M.Zh. Tolyzbekov et al., On the conditions of selective reduction in the Fe – Mn – O system, Bulletin of E. Buketova KarGU, Chemistry series (2005) 4, 65-70.
- [8] B. K. Kassenov, Sh. B. Kassenova, Zh. I. Sagintaeva et al., Thermodynamic research of new nanodimensional cobalt(nickel)-cuprate-manganites of lanthanum and sodium of $\text{LaNa}_2\text{CoCuMnO}_6$, $\text{LaNa}_2\text{NiCuMnO}_6$, Metallurgija 59 (2020) 1, 133-136.
- [9] B. K. Kassenov, Sh. B. Kassenova, Zh. I. Sagintaeva et al., Thermodynamic and electrophysical properties nanosized cobalt-cuprate-manganite and nickelite-cuprate-manganite oxides, Metallurgija 59 (2020) 3, 407-410.
- [10] B. K. Kassenov, S.T. Edilbayeva, E. S. Mustafin et al., Evaluation of thermodynamic functions of triple oxides of $\text{LnMeMn}_2\text{O}_5$ ($\text{Ln} - \text{rare earth metals, M} - \text{alkali metal}$), Journal of Physical Chemistry 73 (1999) 6, 1116-1118.
- [11] A. T. Oralova, B. K. Kassenov, S. T. Edilbayeva et al., Evaluation of the thermodynamic properties of manganites of $\text{LnMe}_3\text{Met}_3\text{Mn}_4\text{O}_{12}$ ($\text{Ln} - \text{La, Nd, Dy}$; $\text{Me} - \text{alkaline, Met} - \text{alkaline earth}$), Bulletin of al-Farabi KazNU, Chemistry series (2007) 2, 150-156.
- [12] Thermal constants of substances, Reference book edited by V. P. Gushko, M.: Nauka, 1981, Issue X, part 1, 300 p.
- [13] Thermal constants of substances, Reference book edited by V. P. Gushko, M.: Nauka, 1982, Issue X, part 2, 444 p.
- [14] Thermal constants of substances, Reference book edited by V. P. Gushko, M.: Nauka, 1979, Issue IX, 576 p.
- [15] Thermal constants of substances, Reference book edited by V.P. Gushko, M.: Nauka, 1978, Issue XIII, part 1, 536 p.
- [16] Thermal constants of substances, Reference book edited by V.P. Gushko, M.: Nauka, 1972, Issue VI, part 1, 370 p.
- [17] Thermal constants of substances, Reference book edited by V.P. Gushko, M.: Nauka, 1974, Issue VII, part 1, 344 p.
- [18] V.N. Kumok, In Sat: Direct and inverse problems of chemical thermodynamics, Novosibirsk: Nauka, 1987, p. 108.

Note: The responsible translator for English language is Issakova Yelena Pavlovna, Karaganda, Kazakhstan