



Modifikacija elektrokemijskih senzora nanočesticama metalnih oksida

A. Paut,^a A. Prkić,^{a*} I. Mitar^b i L. Guć^b

^a Sveučilište u Splitu, Kemijsko-tehnološki fakultet, Ul. Ruđera Boškovića 35, 21 000 Split

^b Sveučilište u Splitu, Prirodoslovno-matematički fakultet, Ul. Ruđera Boškovića 33, 21 000 Split

Sažetak

Elektrokemijski senzori su zbog svoje jednostavnosti izrade i upotrebe u kontinuiranom razvoju već više od stoljeća te su brojnim modifikacijama dosegli brojna poboljšanja, što se posebno odnosi na povećanje osjetljivosti i selektivnosti, proširenje linearne dinamičke područja te sniženje granice dokazivanja analita. Spomenuta poboljšanja posljedica su noviteta u samoj izvedbi i izgledu elektrokemijskih senzora, kao i sve češće uporabe različitih nanomaterijala kao modifikatora. Među najčešće upotrebljavanim modifikatorima su upravo nanočestice metalnih oksida koje se u senzorima pojavljuju samostalno ili u kombinaciji s drugim materijalima. Posebno se ističe kombinacija nanočestica metalnih oksida i grafena ili (reduciranog) grafskog oksida. Navedena dva materijala sinergijski djeluju s obzirom na to da su grafski slojevi zaduženi za bolju električnu vodljivost, a nanočestice metalnih oksida za sprječavanje njihove agregacije. Također, česta je i kombinacija s višeslojnim ili jednoslojnim ugljikovim nanočevićima te nanočesticama metala. Postoje radovi u kojima su kombinirane različite vrste nanočestica metalnih oksida, što je posebno istaknuto kod kombinacije Al_2O_3 i ZnO . Osim aluminijeva i cinkova oksida, u ovom radu je prikazan pregled literature upotrebljavanih nanočestica željezovih i bakrovinih oksida u procesu modifikacije elektrokemijskih senzora. Uz to, prikazani su podatci o analitu, metode određivanja, linearne dinamičko područje senzora te granica dokazivanja analita. Očit je širok spektar vrsta analita čije je određivanje moguće ovakvim vrstama senzora kao i širok spektar elektroanalitičkih metoda koje su prilikom toga primjenjivane. Ipak, među metodama su najzastupljenije voltametrijske, dok je potenciometrijska metoda primjenjivana u svega nekoliko referencija.

Ključne riječi

Elektrokemijski senzori, nanočestice metalnih oksida, nanočestice željezovih oksida, nanočestice aluminijeva oksida, nanočestice cinkova oksida, nanočestice bakrovinih oksida

1. Uvod

Elektrokemijski senzori imaju sposobnost pretvorbe entalpije elektrokemijske reakcije koja se odvija između analita i samog senzora u koristan signal te se mogu primijeniti kao voltametrijski, amperometrijski i potenciometrijski senzori.^{1,2} Takvi senzori kontinuirano se razvijaju više od stoljeća³ te su im dugoročan razvoj, uz kombinaciju s razvojem drugih tehnoloških i znanstvenih područja, omogućili širok spektar primjene. Osim što su prisutni u svakodnevnoj laboratorijskoj praksi u obliku pH elektroda, upotrebljavaju se u analizi lijekova,⁴ određivanju koncentracije metala u realnim uzorcima,⁴ industriji hrane,⁵ kao biosenzori,⁶ kao senzori za detekciju onečišćenja zraka⁷ i dr.

U svrhu poboljšanja karakteristika elektrokemijskih senzora poput povećanja osjetljivosti i selektivnosti, sniženja granica detekcije i kvantifikacije te proširenja linearne dinamičke područja senzora, često se modifikuju različitim vrstama nanomaterijala i to u najvećoj mjeri nanočesticama (NP) metalnih oksida i nanospojevima ugljika.⁸ Oni se u elektrokemijskim senzorima mogu naći u obliku čvrstog kontakta, raspršeni izravno u sastavu ionsko-selektivne membrane, kao podloga za imobilizaciju ionofora ili kao receptori u biosenzorima.⁹ Među brojnim vrstama na-

nočestica metalnih oksida, nanočestice željezovih oksida, posebno hematit ($\alpha\text{-Fe}_2\text{O}_3$), maghemit ($\gamma\text{-Fe}_2\text{O}_3$) i magnetit (Fe_3O_4), jedne su od najčešće upotrebljavanih u modifikaciji senzora^{10,11} i to zahvaljujući učinkovitijem prijenosu naboja.¹² Pregledom literature očita je upotreba nanočestica i nekih drugih metalnih oksida poput aluminijeva oksida (Al_2O_3), cinkova oksida (ZnO), bakrovinih oksida (CuO i Cu_2O) te je upravo za njih u ovom radu prikazan pregled literature koji uključuje prikaz analita, sastav elektrode, linearne dinamičke područje senzora (LDP), vrijednost granice detekcije (GD) te metodu (M) koja je u predstavljenom radu primjenjivana. S obzirom na to da su istraživanja elektrokemijskih senzora najčešće povezana s voltametrijskim (V) metodama, uključujući diferencijalnu pulsnu voltametriju (DPV), cikličku voltametriju (CV), voltametriju linearne promjene potencijala (LSV) te voltametriju kvadratnih valova (SWV), uporaba spomenutih nanočestica znatno se češće pojavljuje u senzorima ispitanim upravo tim metodama, dok su one znatno manje zastupljene u senzorima testiranim amperometrijskim (A) i potenciometrijskim (P) metodama.

Priroda analita koje je moguće odrediti senzorima modifikiranim nanočesticama metalnih oksida je raznolika, pa tako uključuje teške metale,¹³ male molekule poput glukozе i vodikova peroksida, veće molekule poput proteina i nukleinskih kiselina¹⁴ i dr.

* Autor za dopisivanje: izv. prof. dr. sc. Ante Prkić
e-pošta: prkic@ktf-split.hr

2. Rasprava

2.1. Modifikacija elektrokemijskih senzora nanočesticama željezovih oksida

Kao što je već spomenuto, vrsta analita čiju je koncentraciju moguće izmjeriti senzorima modificiranim nanočesticama željezovih oksida je raznolika, a pregled literature u kojoj su kao modifikatori upotrebljavane nanočestice Fe_2O_3 prikazan je u tablici 1. Metale poput Zn^{2+} , Cd^{2+} i Pb^{2+} određivali su *Lee i sur.*¹⁵ voltametrijskom metodom primjenjujući nanokompoziciju željezova oksida (maghemita) i grafena (G) u kombinaciji s bizmutom. Spomenuta kompozicija iskorištena je za modifikaciju elektrode od staklastog ugljika (GCE) te je ona pokazala visoku selektivnost prema spomenutim analitima kao i mogućnost njihova određivanja u realnim uzorcima pitke vode. Upotrijebljenu kombinaciju željezova oksida i grafena opravdali su njihovim povolnjim sinergijskim djelovanjem, gdje je grafen utjecao na bolju električnu vodljivost, a nanočestice Fe_2O_3 sprječile su agregaciju grafenskih slojeva. Autori smatraju da je ta kombinacija osigurala povoljne vodljive puteve na površini elektrode, te na taj način doprinijela zadovoljavajućem elektrokemijskom ponašanju. Nanokompoziciju reduciranih grafena (rG) i željezova(III) oksida za modifikaciju GCE primjenjivali su *Yu i sur.*¹⁶ ali je u njihovom istraživanju umjesto faze maghemita potvrđena faza hematita, a elektroda je upotrebljavana za određivanje askorbinske kiseline. I u ovom istraživanju istaknut je povoljan međusobni utjecaj nanočestica Fe_2O_3 i G. Osim G, pregledom literature je utvrđena učestala uporaba kompozicije Fe_2O_3 i reduciranih grafenova oksida (rGO) u procesu modifika-

cije GCE,^{17–19} ali kod tih istraživanja nije jasno istaknuto o kojoj je kristalnoj fazi željezova oksida riječ. Spomenutom kombinacijom *Radhakrishnan i sur.*¹⁷ određivali su nitrit, *Wu i sur.*¹⁸ rutin te *Hu i sur.* honokiol i magnolol.¹⁹

U kombinaciji s nanočesticama Fe_2O_3 često se upotrebljavaju i ugljikove nanocjevčice (CNTs), bilo da je riječ o jednoslojnim (SWCNTs) ili višeslojnim (MWCNTs). *Adekunle i sur.*²⁰ upotrijebili su kombinaciju SWCNTs i Fe_2O_3 za određivanje dopamina, dok su *Abdel-Haleem i sur.*²¹ modifikacijom s MWCNTs određivali ivabradin. Autori²¹ su pripremili šest različitih senzora te je najbolje karakteristike pokazao senzor s dodatkom 5 % modifikatora (Fe_2O_3 @MWCNTs). Vodikov peroksid određivali su *Hrbac i sur.*²² i *Yuan i sur.*²³ te su obje skupine autora upotrijebile Fe_2O_3 kao samostalni modifikator, pri čemu su zabilježene niske vrijednosti GD.

Kombinacija amorfognog željezova oksida i nanočestica srebra upotrijebljena je za određivanje nitrata²⁴ te je uočeno da dodatak nanočestica metala ima povoljan učinak na redukciju nitrata.

Iako se u brojnim publikacijama spominje modifikacija senzora nanočesticama željezova oksida u obliku Fe_2O_3 , samo je u nekoliko njih potvrđeno da je zaista riječ o čistoj fazi hematita ($\alpha\text{-Fe}_2\text{O}_3$) ili maghemita ($\gamma\text{-Fe}_2\text{O}_3$), dok su u nekim publikacijama nanočestice željezovih oksida referirane kao Fe_xO_y , čime nije specificirano o kojoj je fazi riječ. *Prkić i sur.*²⁵ elektrodu su modificirali nanočesticama Fe_xO_y i ZnO , a upotrijebljivali su ju za određivanje klorida. Znatno bolja svojstva pokazao je senzor s nanočesticama

Tablica 1 – Pregled literature o uporabi nanočestica Fe_2O_3 u modifikaciji elektrokemijskog senzora

Table 1 – Review of the literature on the use of Fe_2O_3 nanoparticles in the modification of an electrochemical sensor

Analit (metoda)	Sastav elektrode	LDP / mol l ⁻¹	GD / mol l ⁻¹	Ref.
Zn^{2+} (V)	$\text{Bi}/\text{Fe}_2\text{O}_3/\text{G}/\text{GCE}$	$\approx (1,53 \cdot 10^{-8} - 1,53 \cdot 10^{-6})$	$\approx 1,68 \cdot 10^{-9}$	15
Cd^{2+} (V)	$\text{Bi}/\text{Fe}_2\text{O}_3/\text{G}/\text{GCE}$	$\approx (8,9 \cdot 10^{-9} - 8,9 \cdot 10^{-7})$	$\approx 7,12 \cdot 10^{-10}$	15
Pb^{2+} (V)	$\text{Bi}/\text{Fe}_2\text{O}_3/\text{G}/\text{GCE}$	$\approx (4,83 \cdot 10^{-9} - 4,83 \cdot 10^{-7})$	$\approx 3,38 \cdot 10^{-10}$	15
Askorbinska kiselina (CV)	$\text{Fe}_2\text{O}_3/\text{G}/\text{GCE}$	$5,7 \cdot 10^{-4} - 3,97 \cdot 10^{-3}$	$5,43 \cdot 10^{-7}$	16
Nitrit (DPV)	$\text{Fe}_2\text{O}_3/\text{rGO}/\text{GCE}$	$5 \cdot 10^{-8} - 7,8 \cdot 10^{-4}$	$1,5 \cdot 10^{-8}$	17
Rutin (DPV)	$\text{Fe}_2\text{O}_3/\text{rGO}/\text{GCE}$	$1,5 \cdot 10^{-8} - 1,8 \cdot 10^{-5}$	$9,8 \cdot 10^{-9}$	18
Honokiol (DPV)	$\text{Fe}_2\text{O}_3\text{-rGO}/\text{GCE}$	$1,5 \cdot 10^{-8} - 3,3 \cdot 10^{-5}$	$9,64 \cdot 10^{-9}$	19
Magnolol (DPV)	$\text{Fe}_2\text{O}_3\text{-rGO}/\text{GCE}$	$7,5 \cdot 10^{-8} - 2,6 \cdot 10^{-5}$	$1,05 \cdot 10^{-8}$	19
Dopamin (SWV)	EPGE-SWCNT- Fe_2O_3	$3,2 \cdot 10^{-6} - 3,18 \cdot 10^{-5}$	$3,6 \cdot 10^{-7}$	20
Ivabradin (P)	$\text{G/NPOE}/\text{Fe}_2\text{O}_3@\text{MWCNTs}/\text{MIP}/\text{CPE}$	$9,8 \cdot 10^{-8} - 1 \cdot 10^{-3}$	$9,8 \cdot 10^{-8}$	21
H_2O_2 (A)	Amorfni $\text{Fe}_2\text{O}_3/\text{CPE}$	$0 - 8,5 \cdot 10^{-3}$	$2 \cdot 10^{-5}$	22
H_2O_2 (A)	$\text{Fe}_2\text{O}_3/\text{ITO}$	$1 \cdot 10^{-6} - 3,6 \cdot 10^{-4}$	$3 \cdot 10^{-7}$	23
<i>N</i> -acetil-L-cistein (LSV)	$\text{Fe}_2\text{O}_3@\text{CoHCF}/\text{csMCPE}$	$1,22 \cdot 10^{-5} - 6,67 \cdot 10^{-5}$	$2,05 \cdot 10^{-7}$	27
<i>N</i> -acetil-L-cistein (A)	$\text{Fe}_2\text{O}_3@\text{CoHCF}/\text{csMCPE}$	$2 \cdot 10^{-5} - 4,32 \cdot 10^{-4}$	$2,09 \cdot 10^{-8}$	27
L-cistein (A)	$\text{Fe}_2\text{O}_3/\text{N-GR}/\text{CPE}$	$2 \cdot 10^{-7} - 4,98 \cdot 10^{-5}$ i $5 \cdot 10^{-5} - 4 \cdot 10^{-4}$	$1 \cdot 10^{-7}$	28
Amonijak (–)	$\alpha\text{-Fe}_2\text{O}_3/\text{CNTs}$	–	–	29
Fe^{3+} (P)	$\alpha\text{-Fe}_2\text{O}_3\text{-FePO}_4\text{-Ag}_2\text{S}/\text{PTFE}$	$1,22 \cdot 10^{-6} - 10^{-2}$	$1,01 \cdot 10^{-6}$	26

Tablica 2 – Pregled literature o uporabi nanočestica Fe_3O_4 u modifikaciji elektrokemijskih senzoraTable 2 – Review of the literature on the use of Fe_3O_4 nanoparticles in the modification of an electrochemical sensor

Analit (metoda)	Sastav elektrode	LDP / mol l ⁻¹	GD / mol l ⁻¹	Ref.
Nitrit (A)	Ag- Fe_3O_4 -GO/GCE	$5 \cdot 10^{-7} - 7,2 \cdot 10^{-4}$ i $7,2 \cdot 10^{-4} - 8,15 \cdot 10^{-3}$	$1,7 \cdot 10^{-7}$	30
Olanzapin (DPV)	Fe_3O_4 @Ag/CPE	$3,9 \cdot 10^{-7} - 1,38 \cdot 10^{-6}$ i $1,38 \cdot 10^{-6} - 3,84 \cdot 10^{-5}$	$1,8 \cdot 10^{-9}$	31
L-cistein (DPV)	Pt- Fe_3O_4 /rGO/GCE	$1 \cdot 10^{-4} - 1 \cdot 10^{-3}$	$1,01 \cdot 10^{-5}$	32
Hidrokinon (A)	AuNPs/ Fe_3O_4 -APTES-GO/GCE	$3 \cdot 10^{-6} - 1,37 \cdot 10^{-4}$	$1,1 \cdot 10^{-6}$	33
Katehol (A)	AuNPs/ Fe_3O_4 -APTES-GO/GCE	$2 \cdot 10^{-6} - 1,45 \cdot 10^{-4}$	$8 \cdot 10^{-7}$	33
As ³⁺ (SWV)	AuNPs/ Fe_3O_4 /GCE	$\approx (1,33 \cdot 10^{-10} - 1,33 \cdot 10^{-8})$	$\approx 1,29 \cdot 10^{-11}$	34
Dopamin (DPV)	Doped PPY/ Fe_3O_4 /rGO/GCE	$7 \cdot 10^{-9} - 2 \cdot 10^{-6}$	$2,33 \cdot 10^{-9}$	35
Katehol (A)	Fe_3O_4 -MWCNT/GCE	$5 \cdot 10^{-7} - 5,5 \cdot 10^{-6}$	$5,38 \cdot 10^{-8}$	36
Glukoza (P)	Glukozna oksidaza na Fe_3O_4 /kitozan kompozitu/MCGCS	$1 \cdot 10^{-6} - 3 \cdot 10^{-2}$	–	37
Izoniazid (P)	Fe_3O_4 /CPE	$1 \cdot 10^{-10} - 10^{-5}$	$3,09 \cdot 10^{-13}$	38
Hidrazin (DPV)	MBCPE/ Fe_3O_4 NPs/DPB	$1 \cdot 10^{-7} - 4 \cdot 10^{-7}$ i $7 \cdot 10^{-7} - 1,2 \cdot 10^{-5}$	$1,8 \cdot 10^{-8}$	39
Klorheksidin diglukonat (SWV)	GCE/ Fe_3O_4 /CS	$2,1 \cdot 10^{-8} - 2,09 \cdot 10^{-7}$	$5,7 \cdot 10^{-9}$	40
Metil paration (SWV)	Fe_3O_4 @ZrO ₂ /MGCE	$7,60 \cdot 10^{-8} - 9,12 \cdot 10^{-5}$	$1,52 \cdot 10^{-8}$	41
Fe ³⁺ (P)	Fe_3O_4 -FePO ₄ -Ag ₂ S/PTFE	$2,44 \cdot 10^{-6} - 10^{-2}$	$1,85 \cdot 10^{-6}$	26

željezova oksida, a metoda koju su primijenili je potencijometrija. Paut i sur.²⁶ prikazali su proces sinteze te detaljne karakterizacije nanočestica hematita i magnetita kao i njihovu uporabu u modifikaciji ionsko-selektivne elektrode za određivanje željezovih(III) kationa. U ispitivanjima su primjenjivali potenciometrijsku metodu iako je ona u takvim istraživanjima vrlo rijetko zastupljena. Predstavljeni senzori pokazali su visoku osjetljivost, široko linearno dinamičko područje te nisku granicu detekcije.

Osim nanočestica Fe_2O_3 , često se kao modifikator upotrebljavaju i nanočestice magnetita (Fe_3O_4) te je zabilježen sličan trend u kontekstu kombinacije s drugim materijalima (tablica 2). Zahvaljujući njihovoj dobroj električnoj vodljivosti, sposobnosti sprječavanja agregacije nanočestica željezovih oksida te povećanja njihove kemijske stabilnosti, slično kao i kod nanočestica Fe_2O_3 i nanočestice magnetita kombinirane su s nanočesticama srebra te su takvi senzori upotrebljavani za određivanje nitrita³⁰ i olanzapina.³¹ Osim nanočestica srebra, u kombinaciji s magnetitom upotrebljavaju se nanočestice i drugih metala poput zlata i platine³² te su predstavljeni senzori upotrebljavani za određivanje katehola i hidrokinona,³³ arsena(III)³⁴ te L-cisteina.³² Nekoliko različitih skupina autora su za modifikaciju elektroda upotrebljavali kombinaciju nanočestica magnetita i rGO. Wang i sur.³⁵ su rGO obložili nanočesticama magnetita koje su potom polimerizirali pirolom koji je dopiran p-toluensulfonskom kiselinom da bi predstavljena kompozicija imala bolju električnu vodljivost te je njome modificiran GCE upotrebljavani za određivanje dopamina. Wang i sur.³² su upotrebljavali kompoziciju Pt- Fe_3O_4 /rGO za modifikaciju GCE-a te njome određivali L-cistein. Slično kao i kod

Fe_2O_3 , i Fe_3O_4 nanočestice se kombiniraju s MWCNTs-om i to za određivanje katehola, što su predstavili Huang i sur.³⁶

Najveći broj radova koji predstavljaju modifikaciju elektrokemijskih senzora nanočesticama magnetita odnosi se na voltametrijske metode. Potenciometrijske metode su najrjeđe zastupljene te su takva istraživanja predstavili Khun i sur.³⁷ i to za određivanje glukoze te Shabani i sur.³⁸ za određivanje izoniazida. Iz predstavljenog pregleda literature očita je raznolika vrsta analita koje je moguće određivati senzorima modificiranim nanočesticama magnetita te činjenica da ih se najčešće upotrebljava u kombinaciji s nekim drugim materijalima.

Pregledom predstavljenje literature te analizom podataka o vrijednostima granice detekcije i linearog dinamičkog područja senzora modificiranih nanočesticama hematita i magnetita uočen je određeni trend. Naime, određivanjem analita voltametrijskim metodama postignute su znatno niže vrijednosti granice detekcije u odnosu na potenciometrijsku metodu. Ipak, potenciometrijsku metodu moguće je primijeniti u širem koncentracijskom području. Među rezultatima prikazanim u tablicama 1 i 2 posebno se ističu vrijednosti GD i LDP senzora sastava Fe_3O_4 /CPE³⁸ koji je, unatoč tome što je primjenjena potenciometrijska metoda, pokazao vrijednost GD-a $3,09 \cdot 10^{-13}$ mol l⁻¹ te LDP-a od 10^{-10} do 10^{-5} mol l⁻¹. Iako je kod većine objavljenih istraživanja primjenjena kombinacija nanočestica hematita ili magnetita s nekim drugim materijalima, očita je i mogućnost uspješnog određivanja analita senzorima modificiranim nanočesticama metalnih oksida ako se upotrebljavaju samostalno.

2.2. Elektrode modificirane nanočesticama aluminijeva oksida (Al_2O_3)

Nanočestice aluminijeva oksida (Al_2O_3) su u odnosu na nanočestice željezovih oksida rjeđe zastupljene u modifikaciji elektrokemijskih senzora. Ipak, postoje istraživanja koja se bave ispitivanjem njihova utjecaja na elektrokemijski odziv prema analitu te su rezultati nekih od njih prikazani u tablici 3. Mekawy i sur.⁴² u svojem su istraživanju predstavili kombinaciju komercijalno dostupnih nanočestica aluminijeva oksida i grafenova oksida (GO) za određivanje koncentracije NADH-a. Autori su prije samog određivanja NADH-a usporedili elektrokemijski signal elektrode Al_2O_3 -GO/CPE s nemodificiranim CPE-om te elektrodom od ugljične paste modificirane nanočesticama srebra, zlata, SWCNTs-om i MWCNTs-om te kompozicijom zlata i GO-a te je upravo elektroda modificirana aluminijevim oksidom pokazala najpovoljnija svojstva. Kombinaciju aluminijeva oksida i rGO-a upotrebljavali su i Li i sur.⁴³ Ta skupina autora je rGO funkcionalizirala vodljivim polimerom (polidialdimetilamonijev klorid, PDDA) da bi se izbjegla njegova agregacija, dok je agregacija dodanih nanočestica zlata sprječena dodatkom nanočestica Al_2O_3 . Na taj je način izrađen senzor sastava Al_2O_3 -Au/PDDA/rGO/GCE uspješno upotrijebljen za određivanje acetaminofena. Nanokompoziciju drugog vodljivog polimera (polianilin, PAn) i γ - Al_2O_3 za modifikaciju elektrode od zlata upotrebljavali su Parvin i sur.⁴⁴ za određivanje vitamina E. Osim kombinacije s ugljikovim materijalima te vodljivim polimerima, u procesu modifikacije elektroda Al_2O_3 kombinira se i s nanočesticama metala i metalnih oksida. Soltani i sur.⁴⁵ modificirali su CPE nanokompozicijom paladija i Al_2O_3 te ju upotrebljavali za određivanje melatonina, dopamina i acetaminofena.

Pregledom literature ustanovljeno je da se nanočestice Al_2O_3 najčešće upotrebljavaju u kombinaciji s nanočesticama cinkova oksida (ZnO). Tom kombinacijom Ganjali i sur.⁴⁶ modificirali su GCE te ju upotrebljavali za određivanje dopamina, dok su druge skupine autora istu kombinaciju upotrebljavale za modifikaciju "screen printed elektroda"

(SPCE) za određivanje metildopa,⁴⁷ hidroklorotiozida,⁴⁷ salicilne⁴⁸ i askorbinske kiseline.⁴⁹ Osim nanočestica hematisita i magnetita, Paut i sur.²⁶ u svojem su istraživanju ispitali i utjecaj nanočestica aluminijeva oksida u različitim postotcima na odziv prema željezovim(III) kationima. U tablici 3 prikazane su vrijednosti za senzor koji u sastavu uključuje 0,5 % nanočestica Al_2O_3 .

Kod modifikacije senzora nanočesticama Al_2O_3 posebno se ističe kombinacija s nanočesticama ZnO te kombinacija s nanočesticama metala, odnosno paladija. Među istraživanjima predstavljenima u tablici 3 ističe se senzor sastava PdNP@ Al_2O_3 /CPE⁴⁵ koji je uspješno upotrijebljen za određivanje tri različita analita te su postignute niske vrijednosti GD-a i to u iznosu od $2,1 \cdot 10^{-8}$, $3,6 \cdot 10^{-9}$ te $2,1 \cdot 10^{-8} \text{ mol l}^{-1}$ redom za melatonin, dopamin i acetaminofen. Kod većine objavljenih istraživanja primijenjena je DPV metoda.

2.3. Elektrode modificirane nanočesticama cinkova oksida

Nanočestice cinkova oksida, u modifikaciji elektroda pojavljuju se u kombinaciji s nanočesticama drugih metalnih oksida, ali i nanočesticama metala te ugljičnim materijalima (tablica 4). Kombinaciju ZnO nanočestica i MWCNTs-a upotrijebili su Tashkhourian i sur.⁵⁰ za određivanje naprosena te Afkhami i sur.⁵¹ za određivanje levodopa. Obje skupine autora modificirale su CPE, ali Afkhami i sur. su ju zbog povećanja selektivnosti dodatno modificirali i s polianilinom. U kombinaciji s ZnO nanočesticama upotrebljavani su i drugi ugljični materijali pa su Kalambate i sur.⁵² upotrijebili G-ZnO-CPE elektrodu za određivanje pirazinamida. Zbog povećanja vodljivosti senzora, ZnO nanočestice se u nekim istraživanjima kombiniraju s nanočesticama zlata. Spomenutu kombinaciju upotrijebili su Ghazizadeh i sur.⁵³ te Hou i sur.⁵⁴ i to za modifikaciju GCE-a, s tim da su Au-ZnO kompoziciju Ghazizadeh i sur. obložili silicijevim dioksidom.

Tablica 3 – Pregled literature o uporabi nanočestica Al_2O_3 u modifikaciji elektrokemijskog senzora

Table 3 – Review of the literature on the use of Al_2O_3 nanoparticles in the modification of an electrochemical sensor

Analit (metoda)	Sastav elektrode	LDP / mol l^{-1}	GD / mol l^{-1}	Ref.
NADH (DPV)	Al_2O_3 -GO/CPE	$3 \cdot 10^{-5} - 3,3 \cdot 10^{-4}$	$4,5 \cdot 10^{-6}$	42
Dopamin (DPV)	ZnO- Al_2O_3 /GCE	$5,0 \cdot 10^{-6} - 7,0 \cdot 10^{-4}$	$2,0 \cdot 10^{-6}$	46
Vitamin E (DPV)	Au/PAn/ γ - Al_2O_3	—	$6 \cdot 10^{-8}$	44
Metildopa (DPV)	ZnO/ Al_2O_3 /SPCE	$1 \cdot 10^{-6} - 1 \cdot 10^{-4}$	$5 \cdot 10^{-7}$	47
Hidroklorotiazid (DPV)	ZnO/ Al_2O_3 /SPCE	$1 \cdot 10^{-7} - 1 \cdot 10^{-4}$	$8 \cdot 10^{-8}$	47
Salicilna kiselina (DPV)	ZnO/ Al_2O_3 /grafitna SPCE	$5 \cdot 10^{-7} - 8 \cdot 10^{-5}$	$2,5 \cdot 10^{-7}$	48
Acetaminofen (DPV)	Al_2O_3 -Au/PDDA/rGO/GCE	$2 \cdot 10^{-8} - 2 \cdot 10^{-4}$	$6 \cdot 10^{-9}$	43
Melatonin (DPV)	PdNP@ Al_2O_3 /CPE	$6 \cdot 10^{-8} - 1,4 \cdot 10^{-4}$	$2,1 \cdot 10^{-8}$	45
Dopamin (DPV)	PdNP@ Al_2O_3 /CPE	$5 \cdot 10^{-8} - 1,45 \cdot 10^{-4}$	$3,6 \cdot 10^{-9}$	45
Acetaminofen (DPV)	PdNP@ Al_2O_3 /CPE	$4 \cdot 10^{-8} - 1,4 \cdot 10^{-4}$	$2,1 \cdot 10^{-8}$	45
Askorbinska kiselina (DPV)	ZnO/ Al_2O_3 nanokompozit/grafitna SPCE	$1 \cdot 10^{-6} - 1 \cdot 10^{-4}$	$6 \cdot 10^{-7}$	49
Fe ³⁺ (P)	Al_2O_3 / FePO_4 / Ag_2S /PTFE	$7,81 \cdot 10^{-5} - 10^{-2}$	$4,87 \cdot 10^{-5}$	26

Tablica 4 – Pregled literature o uporabi nanočestica ZnO u modifikaciji elektrokemijskog senzora

Table 4 – Review of the literature on the use of ZnO nanoparticles in the modification of an electrochemical sensor

Analit (metoda)	Sastav elektrode	LDP / mol l ⁻¹	GD / mol l ⁻¹	Ref.
Naproksen (SWV)	ZnO/MWCNT/CPE	1 · 10 ⁻⁶ – 2 · 10 ⁻⁴	2,3 · 10 ⁻⁷	50
L-dopa (DPV)	PG/ZnO/CNTs/CPE	5 · 10 ⁻⁶ – 5 · 10 ⁻⁴	8 · 10 ⁻⁸	51
Pirazinamid (DPV)	G-ZnO-CPE	1,5 · 10 ⁻⁷ – 4 · 10 ⁻⁴	4,31 · 10 ⁻⁸	52
4-nitrofenol (DPV)	Au-ZnO-SiO ₂ /GCE	1 · 10 ⁻⁸ – 1,2 · 10 ⁻⁶	2,8 · 10 ⁻⁹	53
Askorbinska kiselina (DPV)	ZnO NRs-Au NPs/GCE	1 · 10 ⁻⁴ – 4 · 10 ⁻³	4,699 · 10 ⁻⁶	54
Mokraćna kiselina (DPV)	ZnONRs-Au NPs/GCE	1 · 10 ⁻⁵ – 4 · 10 ⁻⁴	2,375 · 10 ⁻⁶	54

Tablica 5 – Pregled literature o uporabi nanočestica CuO i Cu₂O u modifikaciji elektrokemijskog senzoraTable 5 – Review of the literature on the use of CuO and Cu₂O nanoparticles in the modification of an electrochemical sensor

Analit (metoda)	Sastav elektrode	LDP / preračunato mol l ⁻¹	GD / preračunato mol l ⁻¹	Ref.
Dopamin (DPV)	CuO/GCE	1 · 10 ⁻⁷ – 1,05 · 10 ⁻⁴	1 · 10 ⁻⁷	55
Hidrazin (DPV)	nano-CuO/modificirana GCE	2,5 · 10 ⁻⁵ – 1,66 · 10 ⁻³	1,2 · 10 ⁻⁵	56
Teofilin (DPV)	CuO-GO/CPE	1 · 10 ⁻⁷ – 3,5 · 10 ⁻⁶	8,33 · 10 ⁻⁹	57
Glukoza (A)	CuO/rGO/Cu ₂ O/Cu	5 · 10 ⁻⁷ – 8,266 · 10 ⁻³	1 · 10 ⁻⁷	58

Povoljan utjecaj Au u kombinaciji s ZnO te SiO₂ očit je s obzirom na izrazito nisku vrijednost GD,⁵³ čak 2,8 · 10⁻⁹ mol l⁻¹. Iako je spomenuta vrijednost među svim vrijednostima prikazanim u tablici 4 najniža, i ostale se prikazane elektrode odlikuju vrlo niskim vrijednostima GD-a, dok su vrijednosti LDP-a od jednog do, otpriklje, tri reda veličine. Svi senzori predstavljeni u tablici 4 testirani su primjenom voltametrijske metode i to je najčešće riječ o DPV metodi.

2.4. Elektrode modificirane nanočesticama bakrova oksida

Bakrovi oksidi, CuO i Cu₂O, zahvaljujući tome što pripadaju p-skupini poluvodiča, naišli su na široku primjenu u elektrokemijskim senzorima¹⁰. U tablici 5 prikazan je pregled literature samo nekih elektroda kod kojih su bakrovi oksidi upotrijebljeni kao modifikatori, samostalno^{55,56} ili u kombinaciji s nekim drugim materijalima. Slično kao i kod prethodno prikazanih elektroda, i bakrovi oksidi se često kombiniraju s (reduciranim) grafenovim oksidom.^{57,58}

Kombinacija nanočestica CuO i GO⁵⁷ omogućila je određivanje teofilina metodom DPV te je ostvarena iznimno niska vrijednost GD-a u iznosu od 8,33 · 10⁻⁹ mol l⁻¹. S druge strane, senzor sastava CuO/rGO/Cu₂O/Cu ističe se najširim LDP-om i to u rasponu od 5 · 10⁻⁷ do 8,266 · 10⁻³ mol l⁻¹.

3. Zaključak

Ovim radom detaljno je prikazana literatura koja sadrži uporabu nanočestica metalnih oksida u modifikaciji elektrokemijskih senzora s prikazom analita, sastava elektrode, linearног dinamičког područja, granice detekcije te me-

tode određivanja. Među različitim vrstama, nanočestice željezovih oksida jedne su od najčešće upotrebljavanih u procesu modifikacije elektrokemijskih senzora, posebno hematit, maghemit i magnetit. Ipak, velik broj radova ne specificira o kojoj je točno fazi željezova oksida riječ. Osim oksida željeza, visoko su u elektrokemijskim senzorima zastupljene i nanočestice cinkova oksida. One, osim što se često upotrebljavaju samostalno, u velikom broju istraživanja pojavljuju se u kombinaciji s nanočesticama aluminijeva oksida. Pregledom literature ustanovljena je vrlo česta kombinacija nanočestica metalnih oksida s uglijčnim materijalima, posebno grafenom i (reduciranim) grafenovim oksidom. Razlog je sinergijsko djelovanje tih dviju komponenti, gdje grafen i njegovi oksidi utječu na povećanje električne vodljivosti, a nanočestice sprječavaju njegovu agregaciju.

Najčešće su modificirane CPE i GCE, dok su SPE nešto rjeđe zastupljene. Metode kojima su određene koncentracije različitih analita u najvećem broju radova su voltametrijske, dok su potenciometrijske metode primjenjene u svega nekoliko radova.

Iz ovog rada očito je da su nanočestice metalnih oksida perspektivni i sve češće upotrebljavani modifikatori za elektrokemijske senzore te ih je moguće upotrebljavati za određivanje širokog spektra različitih vrsta analita u širokom koncentracijskom području.

ZAHVALA

Ovaj pregledni rad izrađen je u sklopu provedbe projekta UIP-2017-05-6282 pod imenom Razvoj novih membrana za ionsko-selektivne elektrode s dodatkom nanočestica metala i metalnih oksida koji financira Hrvatska zaklada za znanost.

Popis kratica**List of abbreviations**

NP	– nanočestice – nanoparticles
LDP	– linearno dinamičko područje – linear dynamic range
GD	– granica detekcije – detection limit
M	– metoda – method
V	– voltametrija – voltammetry
DPV	– diferencijalna pulsna voltametrija – differential pulse voltammetry
CV	– ciklička voltametrija – cyclic voltammetry
LSV	– voltametrija linearne promjene potencijala – linear sweep voltammetry
SWV	– voltametrija kvadratnih valova – square wave voltammetry
A	– amperometrija – amperometry
P	– potenciometrija – potentiometry
G	– grafen – graphene
rG	– reducirani grafen – reduced graphene
rGO	– reducirani grafenov oksid – reduced graphene oxide
CNTs	– ugljične nanocijevi – carbon nanotubes
MWCNTs	– višestjenčane ugljikove nanocjevčice – multi walled carbon nanotubes
SWCNT	– jednoslojne ugljične cijevi – single wall carbon nanotubes
EPGE	– pirolitička grafitna elektroda rubne ravnine – edge-plane pyrolytic graphite electrode
NPOE	– nitrofeniloktil eter – nitrophenyloctyl ether
MIP	– molekularno utisnuti polimer – molecularly imprinted polymer
ITO	– indijev kositar oksid – indium tin oxide
SPCE	– printane elektrode – screen printed electrode
CoHCF	– kobaltov heksacijanoferat – cobalt hexacyanoferrate
CsMCPE	– modificirana elektroda od ugljične paste – modified carbon paste electrode
N-GR	– N-dopirani grafen – N-doped graphene
GO	– grafenov oksid – graphene oxide
CPE	– elektroda od ugljične paste – carbon paste electrode

APTES-3	– aminopropil trietoksilan – aminopropyl triethoxysilane
MBCPE	– magnetna šipka elektrode od ugljične paste – magnetic bar carbon paste electrode
MGCCS	– modificirana pozlaćena staklena podloga – modified gold coated glass substrate
DPB	– 2-(3,4-dihidroksifenil) benzotiazol – 2-(3,4-dihydroxyphenyl) benzothiazole
CS	– kitozan – chitosan
MGCE	– magnetična elektroda od staklastog ugljika – magnetic glassy carbon electrode
PDDA	– poli(dialildimetilamonijev klorid) – poly(diallyldimethylammonium chloride)
PAn	– polianilin – polyaniline
PG	– poliglicin – polyglycine
PTFE	– politetrafluoroetilen – polytetrafluoroethylene
NRs	– nanoštapići – nanorods

Literatura
References

1. P. Gründler, Chemical sensors. An introduction for scientists and engineers, Springer, Verlag Berlin Heidelberg, 2007., str. 1–13, 137–196.
2. A. Hulanicki, S. Glab, F. Ingman, Chemical sensors: definitions and classification, Pure Appl. Chem. **63** (1991) 1247–1250, doi: <https://doi.org/10.1351/pac199163091247>.
3. K. H. Lubert, K. Kalcher, History of electroanalytical methods, Electroanalysis **22** (2010) 1937–1946, doi: <https://doi.org/10.1002/elan.201000087>.
4. Ö. Isildak, O. Özbeş, Application of Potentiometric Sensors in Real Samples, Crit. Rev. Anal. Chem. **51** (2021) 218–231, doi: <https://doi.org/10.1080/10408347.2019.1711013>.
5. K. Sharifi, S. Pirsa, Electrochemical sensors; Types and applications in the food industry, **3** (2020) 192–201, doi: <https://doi.org/10.22034/crl.2020.240962.1073>.
6. I.-H. Cho, D. H. Kim, S. Park, Electrochemical biosensors: perspective on functional nanomaterials for on-site analysis, **24** (2020) 6, doi: <https://doi.org/10.1186/s40824-019-0181-y>.
7. E. S. Cross, L. R. Williams, D. K. Lewis, G. R. Magoon, T. B. Onasch, M. L. Kaminsky, D. R. Worsnop, J. T. Jayne, Use of electrochemical sensors for measurement of air pollution: correcting interference response and validating measurements, Atmos. Meas. Tech. **10** (2017) 3575–3588, doi: <https://doi.org/10.5194/amt-10-3575-2017>.
8. N. Baig, M. Sajid, T. A. Saleh, Recent trends in nanomaterial-modified electrodes for electroanalytical applications, TrAC – Trends Anal. Chem. **111** (2019) 47–61, doi: <https://doi.org/10.1016/j.trac.2018.11.044>.
9. T. Yin, W. Qin, Applications of nanomaterials in potentiometric sensors, TrAC - Trends Anal. Chem. **51** (2013) 79–86, doi: <https://doi.org/10.1016/j.trac.2013.06.009>.
10. J. M. George, A. Antony, B. Mathew, Metal oxide nanoparticles in electrochemical sensing and biosensing: a review, Mi-

- crochim. Acta **185** (2018) 358, doi: <https://doi.org/10.1007/s00604-018-2894-3>.
11. V. H. Grassian, When size really matters: size-dependent properties and surface chemistry of metal and metal oxide nanoparticles in gas and liquid phase environments, J. Phys. Chem. C **112** (2008) 18303–18313, doi: <https://doi.org/10.1021/jp806073t>.
 12. A. S. Agnihotri, A. Varghese, M. Nidhin, Transition metal oxides in electrochemical and bio sensing: A state-of-art review, Appl. Surf. Sci. Adv. **4** (2021) 100072, doi: <https://doi.org/10.1016/j.apsadv.2021.100072>.
 13. S. Sawan, R. Maalouf, A. Errachid, N. Jaffrezic-Renault, Metal and metal oxide nanoparticles in the voltammetric detection of heavy metals: A review, TrAC – Trends Anal. Chem. **131** (2020) 116014, doi: <https://doi.org/10.1016/j.trac.2020.116014>.
 14. W. Q. Lim, Z. Gao, Metal oxide nanoparticles in electroanalysis, Electroanalysis **27** (2015) 2074–2090, doi: <https://doi.org/10.1002/elan.201500024>.
 15. S. Lee, J. Oh, D. Kim, Y. Piao, A sensitive electrochemical sensor using an iron oxide/graphene composite for the simultaneous detection of heavy metal ions, Talanta **160** (2016) 528–536, doi: <https://doi.org/10.1016/j.talanta.2016.07.034>.
 16. Z. Yu, H. Li, J. Lu, X. Zhang, N. Liu, X. Zhang, Hydrothermal synthesis of Fe_2O_3 /graphene nanocomposite for selective determination of ascorbic acid in the presence of uric acid, Electrochim. Acta **158** (2015) 264–270, <https://doi.org/10.1016/j.electacta.2015.01.131>.
 17. S. Radhakrishnan, K. Krishnamoorthy, C. Sekar, J. Wilson, S. J. Kim, A highly sensitive electrochemical sensor for nitrite detection based on Fe_2O_3 nanoparticles decorated reduced graphene oxide nanosheets, Appl. Catal. B **148–149** (2014) 22–28, <https://doi.org/10.1016/j.apcatb.2013.10.044>.
 18. Y. Wu, C. Hu, M. Huang, N. Song, W. Hu, Highly enhanced electrochemical responses of rutin by nanostructured Fe_2O_3 /RGO composites, Ionics **21** (2015) 1427–1434, doi: <https://doi.org/10.1007/s11581-014-1310-1>.
 19. W. Hu, W. Zhang, Y. Wu, W. Qu, Self-assembly and hydrothermal technique synthesized Fe_2O_3 -RGO nanocomposite: The enhancement effect of electrochemical simultaneous detection of honokiol and magnolol, J. Electroceram. **40** (2018) 1–10, doi: <https://doi.org/10.1007/s10832-017-0075-0>.
 20. A. S. Adekunle, B. O. Agboola, J. Pillay, K. I. Ozoemena, Electrocatalytic detection of dopamine at single-walled carbon nanotubes–iron (III) oxide nanoparticles platform, Sensor. Actuat. B – Chem. **148** (2010) 93–102, doi: <https://doi.org/10.1016/j.snb.2010.03.088>.
 21. F. M. Abdel-Haleem, E. Gamal, M. S. Rizk, A. Madbouly, R. M. El Nashar, B. Anis, H. M. Elnabawy, A. S. G. Khalil, A. Barhoum, Molecularly Imprinted Electrochemical Sensor-Based Fe_2O_3 @MWCNTs for Ivabradine Drug Determination in Pharmaceutical Formulation, Serum, and Urine Samples, Front. Bioeng. Biotechnol. **9** (2021) 648704, doi: <https://doi.org/10.3389/fbioe.2021.648704>.
 22. J. Hrbac, V. Halouzka, R. Zboril, K. Papadopoulos, T. Triantis, Carbon Electrodes Modified by Nanoscopic Iron(II) Oxides to Assemble Chemical Sensors for the Hydrogen Peroxide Amperometric Detection, Electroanalysis **19** (2007) 1850–1854, <https://doi.org/10.1002/elan.200703938>.
 23. M. Yuan, J. Li, Y. Yu, Y. Fu, A. Fong, J. Hu, Fabrication of a Fe_2O_3 Nanoparticles Implantation-modified Electrode and its Applications in Electrochemical Sensing, Electroanalysis **28** (2015) 954–961, doi: <https://doi.org/10.1002/elan.201500585>.
 24. M. Bonyani, A. Mirzaei, S. G. Leonardi, A. Bonavita, G. Neri, Electrochemical Properties of Ag@iron Oxide Nanocomposite for Application as Nitrate Sensor, Electroanalysis **27** (2015) 2654–2662, <https://doi.org/10.1002/elan.201500240>.
 25. A. Prkic, T. Vukusic, I. Mitar, J. Giljanovic, V. Sokol, P. Boskovic, M. Jakic, A. Sedlar, New sensor based on AgCl containing Iron Oxide or Zinc Oxide Nanoparticles for Chloride Determination, Int. J. Electrochem. Sc. **14** (2019) 861–874, doi: <https://doi.org/10.20964/2019.01.71>.
 26. A. Paut, A. Prkić, I. Mitar, L. Guć, M. Marciuš, M. Vrankić, S. Krehula, L. Tomaško, The New Ion-Selective Electrodes Developed for Ferric Cations Determination, Modified with Synthesized Al and Fe−, Based Nanopart. **22** (2022) 297, doi: <https://doi.org/10.3390/s22010297>.
 27. H. Heli, S. Majdi, N. Sattarahmady, Ultrasensitive sensing of N-acetyl-L-cysteine using an electrocatalytic transducer of nanoparticles of iron(III) oxide core–cobalt hexacyanoferate shell, Sensor. Acutat. B – Chem. **145** (2010) 185–193, <https://doi.org/10.1016/j.snb.2009.11.065>.
 28. S. Yang, G. Li, G. Wang, D. Deng, L. Qu, A novel electrochemical sensor based on Fe_2O_3 nanoparticles/N-doped graphene for electrocatalytic oxidation of L-cysteine, J. Solid State Electrochem. **19** (2015) 3613–3620, doi: <https://doi.org/10.1007/s10008-015-2980-y>.
 29. P. Muthukumaran, C. Sumathi, J. Wilson, C. Sekar, S. Leonardi, G. Neri, Fe_2O_3 /Carbon nanotube-based resistive sensors for the selective ammonia gas sensing, Sens. Lett. **12** (2014) 17–23, doi: <https://doi.org/10.1166/sl.2014.3220>.
 30. B.-Q. Li, F. Nie, Q.-L. Sheng, J.-B. Zheng, An electrochemical sensor for sensitive determination of nitrites based on Ag– Fe_2O_4 –graphene oxide magnetic nanocomposites, Chem. Pap. **69** (2015) 911–920, doi: <https://doi.org/10.1515/chempap-2015-0099>.
 31. M. Arvand, S. Orangpour, N. Ghodsi, Differential pulse stripping voltammetric determination of the antipsychotic medication olanzapine at a magnetic nano-composite with a core/shell structure, RSC Adv. **5** (2015) 46095–46103, doi: <https://doi.org/10.1039/C5RA00061K>.
 32. Y. Wang, W. Wang, G. Li, Q. Liu, T. Wei, B. Li, C. Jiang, Y. Sun, Electrochemical detection of L-cysteine using a glassy carbon electrode modified with a two-dimensional composite prepared from platinum and Fe_3O_4 nanoparticles on reduced graphene oxide, Microchim. Acta **183** (2016) 3221–3228, doi: <https://doi.org/10.1007/s00604-016-1974-5>.
 33. S. Erogul, S. Z. Bas, M. Ozmen, S. Yildiz, A new electrochemical sensor based on Fe_3O_4 functionalized graphene oxide–gold nanoparticle composite film for simultaneous determination of catechol and hydroquinone, Electrochim. Acta **186** (2015) 302–313, <https://doi.org/10.1016/j.electacta.2015.10.174>.
 34. H. Cui, W. Yang, X. Li, H. Zhao, Z. Yuan, An electrochemical sensor based on a magnetic Fe_3O_4 nanoparticles and gold nanoparticles modified electrode for sensitive determination of trace amounts of arsenic(III), Anal. Methods **4** (2012) 4176–4181, doi: <https://doi.org/10.1039/C2AY25913C>.
 35. Y. Wang, Y. Zhang, C. Hou, M. Liu, Ultrasensitive electrochemical sensing of dopamine using reduced graphene oxide sheets decorated with p-toluenesulfonate-doped polypyrrole/ Fe_3O_4 nanospheres, Microchim. Acta **183** (2016) 1145–1152, doi: <https://doi.org/10.1007/s00604-016-1742-6>.
 36. H. Huang, X. Liu, X. Zhang, W. Liu, X. Su, Z. Zhang, Fabrication of New Magnetic Nanoparticles (Fe_3O_4) Grafted Multiwall Carbon Nanotubes and Heterocyclic Compound Modified Electrode for Electrochemical Sensor, Electroanalysis **22** (2010) 433–438, <https://doi.org/10.1002/elan.200900335>.

37. K. Khun, Z. H. Ibupoto, J. Lu, M. S. Alsalhi, M. Atif, A. A. Ansari, M. Willander, Potentiometric glucose sensor based on the glucose oxidase immobilized iron ferrite magnetic particle/chitosan composite modified gold coated glass electrode, *Sensor. Actuat. B - Chem.* **173** (2012) 698–703, <https://doi.org/10.1016/j.snb.2012.07.074>.
38. R. Shabani, Z. Lakhay Rizi, R. Moosavi, Selective Potentiometric Sensor for Isoniazid Ultra-Trace Determination Based on Fe₃O₄ Nanoparticles Modified Carbon Paste Electrode (Fe₃O₄/CPE), *Int. J. Nanosci. Nanotechnol.* **14** (2018) 241–249.
39. A. Benvidi, S. Jahanbani, B.-F. Mirjalili, R. Zare, Electrocatalytic oxidation of hydrazine on magnetic bar carbon paste electrode modified with benzothiazole and iron oxide nanoparticles: Simultaneous determination of hydrazine and phenol, *Chin. J. Catal.* **37** (2016) 549–560, doi: [https://doi.org/10.1016/s1872-2067\(15\)61046-4](https://doi.org/10.1016/s1872-2067(15)61046-4).
40. C. P. Sousa, R. C. de Oliveira, T. M. Freire, P. B. A. Fechine, M. A. Salvador, P. Homem-de-Mello, S. Morais, P. de Lima-Neto, A. N. Correia, Chlorhexidine digluconate on chitosan-magnetic iron oxide nanoparticles modified electrode: Electroanalysis and mechanistic insights by computational simulations, *Sens. Actuat. B* **240** (2017) 417–425, <https://doi.org/10.1016/j.snb.2016.08.181>.
41. N.-N. Li, T.-F. Kang, J.-J. Zhang, L.-P. Lu, S.-Y. Cheng, Fe₃O₄@ZrO₂ magnetic nanoparticles as a new electrode material for sensitive determination of organophosphorus agents, *Anal. Methods* **7** (2015) 5053–5059, doi: <https://doi.org/10.1039/C5AY00314H>.
42. M. M. Mekawy, R. Y. A. Hassan, P. Ramnani, X. J. Yu, A. Mulchandani, Electrochemical detection of dihydronicotinamide adenine dinucleotide using Al₂O₃-GO nanocomposite modified electrode, *Arab. J. Chem.* **11** (2018) 942–949, doi: <https://doi.org/10.1016/j.arabjc.2018.03.017>.
43. J. B. Li, W. Y. Sun, X. J. Wang, H. M. Duan, Y. H. Wang, Y. L. Sun, C. F. Ding, C. N. Luo, Ultra-sensitive film sensor based on Al₂O₃-Au nanoparticles supported on PDDA-functionalized graphene for the determination of acetaminophen, *Anal. Bioanal. Chem.* **408** (2016) 5567–5576, doi: <https://doi.org/10.1007/s00216-016-9654-1>.
44. M. H. Parvin, J. Arjomandi, J. Y. Lee, γ-Al₂O₃ nanoparticle catalyst mediated polyaniline gold electrode biosensor for vitamin E, *Catal. Commun.* **110** (2018) 59–63, doi: <https://doi.org/10.1016/j.catcom.2018.03.009>.
45. N. Soltani, N. Tavakkoli, F. Shahdost-fard, H. Salavati, F. Abdolli, A carbon paste electrode modified with Al₂O₃-supported palladium nanoparticles for simultaneous voltammetric determination of melatonin, dopamine, and acetaminophen, *Microchim. Acta* **186** (2019) 540, doi: <https://doi.org/10.1007/s00604-019-3541-3>.
46. M. Reza Ganjali, Voltammetric Determination of Dopamine Using Glassy Carbon Electrode Modified with ZnO/Al₂O₃ Nanocomposite, *Int. J. Electrochem. Sci.* **13** (2018) 2519–2529, doi: <https://doi.org/10.20964/2018.03.11>.
47. R. Zaimbashi, H. Beitollahi, M. Torkzadeh-Mahani, Simultaneous Electrochemical Sensing of Methyl-dopa and Hydrochlorothiazide using a Novel ZnO/Al₂O₃ Nanocomposite Modified Screen Printed Electrode, *Anal. Bioanal. Electro-* **9** (2017) 1008–1020.
48. M. Reza Ganjali, Determination of Salicylic Acid by Differential Pulse Voltammetry Using ZnO/Al₂O₃ Nanocomposite Modified Graphite Screen Printed Electrode, *Int. J. Electrochem. Sci.* **12** (2017) 9972–9982, doi: <https://doi.org/10.20964/2017.11.49>.
49. M. Reza Ganjali, Highly Sensitive Voltammetric Sensor for Determination of Ascorbic Acid Using Graphite Screen Printed Electrode Modified with ZnO/Al₂O₃ Nanocomposite, *Int. J. Electrochem. Sci.* **12** (2017) 3231–3240, doi: <https://doi.org/10.20964/2017.04.07>.
50. J. Tashkhourian, B. Hemmateenejad, H. Beigizadeh, M. Hosseini-Sarvari, Z. Razmi, ZnO nanoparticles and multiwalled carbon nanotubes modified carbon paste electrode for determination of naproxen using electrochemical techniques, *J. Electroanal. Chem.* **714–715** (2014) 103–108, doi: <https://doi.org/10.1016/j.jelechem.2013.12.026>.
51. A. Afkhami, F. Kafrashi, T. Madrakian, Electrochemical determination of levodopa in the presence of ascorbic acid by polyglycine/ZnO nanoparticles/multi-walled carbon nanotubes-modified carbon paste electrode, *Ionics* **21** (2015) 2937–2947, doi: <https://doi.org/10.1007/s11581-015-1486-z>.
52. P. K. Kalambate, C. R. Rawool, A. K. Srivastava, Voltammetric determination of pyrazinamide at graphene-zinc oxide nanocomposite modified carbon paste electrode employing differential pulse voltammetry, *Sens. Actuat. B: Chem.* **237** (2016) 196–205, <https://doi.org/10.1016/j.snb.2016.06.019>.
53. A. J. Ghazizadeh, A. Afkhami, H. Bagheri, Voltammetric determination of 4-nitrophenol using a glassy carbon electrode modified with a gold-ZnO-SiO₂ nanostructure, *185* (2018) 296, doi: <https://doi.org/10.1007/s00604-018-2840-4>.
54. C. Hou, H. Liu, D. Zhang, C. Yang, M. Zhang, Synthesis of ZnO nanorods-Au nanoparticles hybrids via in-situ plasma sputtering-assisted method for simultaneous electrochemical sensing of ascorbic acid and uric acid, *J. Alloys Compd.* **666** (2016) 178–184, <https://doi.org/10.1016/j.jallcom.2016.01.092>.
55. S. Sundar, G. Venkatachalam, S. Kwon, Biosynthesis of Copper Oxide (CuO) Nanowires and Their Use for the Electrochemical Sensing of Dopamine, *Nanomaterials* **8** (2018) 823, doi: <https://doi.org/10.3390/nano8100823>.
56. J. B. Raoof, R. Ojani, F. Jamali, S. R. Hosseini, Electrochemical detection of hydrazine using a copper oxide nanoparticle modified glassy carbon electrode, *Caspian J. Chem.* **1** (2012) 73–85.
57. V. B. Patil, S. J. Malode, S. N. Mangasuli, S. M. Tuwar, K. Mondal, N. P. Shetti, An Electrochemical Electrode to Detect Theophylline Based on Copper Oxide Nanoparticles Composited with Graphene Oxide, *Micromachines* **13** (2022) 1166, doi: <https://doi.org/10.3390/mi13081166>.
58. C. Zhao, X. Wu, P. Li, C. Zhao, X. Qian, Hydrothermal deposition of CuO/rGO/Cu₂O nanocomposite on copper foil for sensitive nonenzymatic voltammetric determination of glucose and hydrogen peroxide, *Microchim. Acta* **184** (2017) 2341–2348, doi: <https://doi.org/10.1007/s00604-017-2229-9>.

SUMMARY

Electrochemical Sensors Modification with Metal Oxide Nanoparticles

Andrea Paut,^a Ante Prkić,^{a*} Ivana Mitar,^b and Lucija Guć^b

Due to their simplicity of manufacture and use, electrochemical sensors have been continuously developed for more than a century, and have achieved numerous improvements, particularly related to increasing sensitivity and selectivity, extending the linear dynamic range, and lowering the limit of detection. The mentioned improvements are the result of innovations in electrochemical sensor design, as well as the more frequent use of different nanomaterials as modifiers. Among the modifiers most frequently used are metal oxide nanoparticles, which are founding sensors alone or in combination with other materials. The combination of metal oxide nanoparticles and graphene or (reduced) graphene oxide is particularly noteworthy. These two materials positively influence each other, as the graphene layers are responsible for better electrical conductivity and the metal oxide nanoparticles for preventing their aggregation. Combinations with multi-walled or single-walled carbon nanotubes and metal nanoparticles are commonly described too. There are publications giving the description of combined different types of metal oxide nanoparticles, which is particularly evident in the combination of Al_2O_3 and ZnO . In addition to aluminium and zinc oxide, this article reviews the literature on iron and copper oxide nanoparticles used in the modification of electrochemical sensors, the analyte, the method of determination, the linear dynamic range of the sensor, and the limit of detection. The types of analytes that can be determined with these sensors are as varied as the methods used. However, among the methods, the voltammetric method is the most represented, while the potentiometric method has been used in only a few references.

Keywords

Electrochemical sensors, nanoparticles of metal oxides, nanoparticles of iron oxides, nanoparticles of aluminium oxide, nanoparticles of zinc oxide, nanoparticles of copper oxides

^a University of Split, Faculty of Chemistry and Technology, Rudera Boškovića 35, 21 000 Split, Croatia

Review

Received October 11, 2022

Accepted November 15, 2022

^b University of Split, Faculty of Science, Rudera Boškovića 33, 21 000 Split, Croatia